INSPECTION REPORT

SCIENCE TEKNİK BELGELENDİRME A.S.

5190243IB02
2022181122

Overall Rating: **Class B1**

Report No: 2022181122
Applicant: **ADO GOLDKANTE GMBH & CO.KG**
Zimmersmühlenweg 14-18, 61440 Oberursel \ Germany
Contact Person: ODA NIMMER
Contact Telephone: +49 6171 632 168
Contact e-mail: o.nimmer@zimmer-rohde.com
Sample Accepted on: 11.11.2022
Report Date: 18.11.2022
Total number of pages: 7 (Pg)

Sample ID : **10-A3020 SKYE FR**

	TEST	METHOD	RESULT
*	**Fire behaviour of building materials and elements Part 1: Classification of building materials Requirements and testing**	**DIN 4102-1**	**PASS**
			B1

Seal

Customer Representative
Merve Nur KIRVELİ

Laboratory Manager
Merve ÖZLÜ

Merkez Mh, Dr.Sadık Ahmet Cd, No 38 / 44 D BAĞCILAR / İSTANBUL
Tel: 0212 702 20 10 Fax: 0212 909 21 10
Web: www.laboratuvar.com E-mail: info@laboratuvar.com

SCIENCE TEKNIK BELGELENDIRME A.S.

It is prohibited to change any and all versions of this document in any manner whatsoever. In case of a conflict between the electronic version (e.g. PDF file) and the original paper version provided by SCIENCE®, the latter will prevail.

SCIENCE Teknik Belgelendirme A.S. disclaim liability for any direct, indirect, consequential or incidental damages that may result from the use of the information or data, or from the inability to use the information or data contained in this document.

The contents of this report may only be transmitted to third parties in its entirety and provided with the copyright notice,prohibition to change, electronic versions' validity notice and disclaimer.

Environment

The requirements and standards apply to equipment intended for use in

X	Residential (domestic) environment
X	Commercial and light-industrial environment
X	Industrial environment
X	Medical environment

Merkez Mh, Dr. Sadık Ahmet Cd, No 38 /44 D BAĞCILAR / İSTANBUL
Tel: 0212 702 20 10 Fax: 0212 909 21 10
Web: www.laboratuvar.com E-mail: info@laboratuvar.com

DIN 4102-1

Scope

The standard applies to the classification of the fire behavior of building materials to assess the risk as a single building material and in combination with other building materials.

Building Material Classes

The building materials are classified according to their fire behavior into the building material classes according to Table 1:

Building Material Classes	Building Inspectorate Designation
A A1 A2	Non-combustible building materials
B B1 B2 B3	Flammable building materials Flame retardant building materials Normally flammable building materials Easilly flammable building materials

Building material class B1

General requirements :

a) Building materials with the exception of outer wall cladding and floor coverings The test represents a model of the fire of an object in a room (eg waste paper basket in a corner of the room) Under this stress, the fire spread must not extend significantly outside the primary fire area and the heat emission must be limited.
b) Exterior wall cladding The test is a model of the flames emerging from a wall opening. Under this load, the spread of fire must not extend significantly outside the primary fire area.
c) Floor coverings The test represents a model of a fire situation in which flames strike from the door opening to an adjacent room. Under this load, the horizontal flame spread and the smoke development must be harmless.

Requirements for classification

Building materials, with the exception of floor coverings, meet the requirements for classification in building material class B1 if they pass the fire pit test and meet the requirements for building material class B2.

Merkez Mh, Dr. Sadık Ahmet Cd, No 38 /44 D BAĞCILAR / İSTANBUL
Tel: 0212 702 20 10 Fax: 0212 909 21 10
Web: www.laboratuvar.com E-mail: info@laboratuvar.com

RESULTS

10-3019 NEVA FR RE

Results of the Numune test (part 1)					
Row -No	Foil-type:	Measurements test specimen			
			10-A3020 SKYE FR		
1	No. of test specimen arrangement according to DIN 4102, part 15 , table 1		--		
2	Max. flame height above bottom edge cm		0:4		
	Time [1] min : s		0:2		
4	Melt through / burn through Time[1] min : s		0:2		
5	Observations on the backside of the specimens Flames/smouldering Time [1] min : s		--		
6	Discolouration Time [1] min : s		x		
7	Burning droplets Start [1] min : s		x		
8	Extent sporadic burning droplets		--		
9	continually falling particles		x		
10	Falling particles which burns Start [1] min : s		x		
11	sporadic falling parts		x		
12	continually falling particles		--		
13	Duration of the burning on the screen bottom (max.) min : s		--		
14	Interference of the burner flame by dripping /falling particles Time [1] min : s		--		
15	Early termination of the test End of burning at the specimen [1] min : s		--		
16	Time of early cancellation of the test [1] min : s		--		

Merkez Mh, Dr. Sadık Ahmet Cd, No 38 /44 D BAĞCILAR / İSTANBUL
Tel: 0212 702 20 10 Fax: 0212 909 21 10
Web: www.laboratuvar.com E-mail: info@laboratuvar.com

Results of the Numune (part 2)					
Row -no.		Measurements Test Specimen			
			10-A3020 SKYE FR		
	Continuous burning after termination of the test				
17	Duration min : s		--		
18	Number of specimens		--		
19	Front side of the specimen		--		
20	Back side of the specimen		--		
21	Flame length cm		--		
	Smouldering after termination of the test				
22	Duration min : s		--		
23	Number of specimens		--		
	Location				
24	Lower half of the specimens		--		
25	Upper half of the specimens		--		
26	Front side of the specimen		--		
27	Backside of the specimen		--		
	Smoke development				
28	≤ 400 % x min		X		
29	> 400 % x min		--		
30	Diagram in appendix		--		
31	Residual lengths		52 57		
	Single values cm		49 51		
32	Average values cm		52.25		
33	Photo of the specimen on page		--		
	Smoke temperature				
34	Maximum value of the averaged values ºC		X		
35	Time [1] min : s		X		
36	Diagram in appendix Nr.		--		

1) Time counting from the start of the test

Merkez Mh, Dr. Sadık Ahmet Cd, No 38 /44 D BAĞCILAR / İSTANBUL
Tel: 0212 702 20 10 Fax: 0212 909 21 10
Web: www.laboratuvar.com E-mail: info@laboratuvar.com

Baustoffklasse B1 (schwerentflammbare Baustoffe)

According to DIN 4102 part 1 (Mai 1998). This assessment is only valid, if the foils are glued on steel. The surface of the self-adhesive foils may be printed, but not be covered with paints, coatings or similar products. The resistance of the fire behaviour against climatic influences in the outside was not proofed. Therefore the product may be used as schwerentflammbar only inside of buildings or in oth- erwise weather protected areas.

- The material does not produce burning droplets / particles.



Merkez Mh, Dr. Sadık Ahmet Cd, No 38 /44 D BAĞCILAR / İSTANBUL
Tel: 0212 702 20 10 Fax: 0212 909 21 10
Web: www.laboratuvar.com E-mail: info@laboratuvar.com

Sample Image

*****End Of Report*****

Merkez Mh, Dr. Sadık Ahmet Cd, No 38 /44 D BAĞCILAR / İSTANBUL
Tel: 0212 702 20 10 Fax: 0212 909 21 10
Web: www.laboratuvar.com E-mail: info@laboratuvar.com