



CERTIFICATE

CENTEXBEL TYPE TESTING | TEST REPORT N° 21.06884.01

According to report N° 21.06884.01, dated on 7/12/2021, we confirm that the below mentioned items were tested at CENTEXBEL with reference to **NF P 92-507 (2004) "Fire safety - Building - Interior fitting materials - Classification according to their reaction to fire"**.

The items show

Classification M1

When properly applied.

The evaluation of the burning behaviour is based on CENTEXBEL's evaluation scheme.

SAMPLES	8000 Various colours
Company	Ado Goldkante GmbH Co Kg Zimmersmühlenweg 14-18 61440 OBERURSEL - GERMANY

This Certificate is valid until 7/12/2026

Centexbel | Technologiepark 70 | BE 9052 Gent | Belgium, 7/12/2021

A handwritten signature in blue ink, appearing to read 'Stijn Devaere'.

Stijn Devaere, PhD
Director Services



ADO Goldkante GmbH & Co. KG
Zimmersmühlenweg 14-18
61440 OBERURSEL
Germany

Your notice of
04-11-2021

Your reference

Date
07-12-2021

Analysis Report 21.06884.01

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2123742	Art. 8000 col. 582	04-11-2021
T2123743	Art. 8000 col. 392	04-11-2021
T2123744	Art. 8000 col. 682	04-11-2021

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T2123742 - Art. 8000 col. 582
T2123743 - Art. 8000 col. 392
T2123744 - Art. 8000 col. 682

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test 26-11-2021
Standard used NF P92-503 (1995)
Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 600 mm x 180 mm x ≤ 1 mm
Weight (g/m²)
T2123742: 123
T2123743: 126
T2123744: 122

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

T2123742

	Length		Width	
	Front	Back	Front	Back
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	15.0	-	-	19.5
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	yes			no
Flaming debris	no			no
Non-flaming debris	no			no

T2123743

	Length		Width	
	Front	Back	Front	Back
Hole formation		yes	yes	
Max. afterflame time (s)	-	0	0	-
Afterglow		no	no	
Afterglow with propagation in area > 25 cm		no	no	
Damaged length (cm)	-	17.5	21.5	-
Damaged width (cm) in area >45 cm	-	0	0	-
Flaming molten droplets		no	no	
Non-flaming molten droplets		yes	yes	
Flaming debris		no	no	
Non-flaming debris		no	no	

T2123744

	Length		Width	
	Front	Back	Front	Back
Hole formation	yes			yes
Max. afterflame time (s)	0	-	-	0
Afterglow	no			no
Afterglow with propagation in area > 25 cm	no			no
Damaged length (cm)	20.0	-	-	15.0
Damaged width (cm) in area >45 cm	0	-	-	0
Flaming molten droplets	no			no
Non-flaming molten droplets	yes			no
Flaming debris	no			no
Non-flaming debris	no			no

Reference: T2123742 - Art. 8000 col. 582
T2123743 - Art. 8000 col. 392
T2123744 - Art. 8000 col. 682

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test	06-12-2021
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	A limited number of specimens have been tested for each sample.
Dimension of the specimens	460 mm x 230 mm x < 1 mm
Weight (g/m ²)	T2123742:123 T2123743:126 T2123744:122

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

Reference: T2123742 - Art. 8000 col. 582
 T2123743 - Art. 8000 col. 392
 T2123744 - Art. 8000 col. 682

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test 07-12-2021
 Standard used NF P92-505 (1995)
 Product standard NF P92-507 (2004)

Deviation from the standard A limited number of specimens have been tested for each sample.

Dimension of the specimens 70 mm x 70 mm x 1 mm
 Number of layers 4
 Weight (g/m²) T2123742:123
 T2123743:126
 T2123744:122

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
 Minimum 7 days or until constant mass is achieved

T2123742

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.4
#2	back	*	yes	no	no	2.5
#3	front					
#4	back					

* no ignition

T2123743

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.6
#2	back	*	yes	no	no	2.5
#3	front					
#4	back					

* no ignition



T2123744

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	2.6
#2	back	*	yes	no	no	2.6
#3	front					
#4	back					

* no ignition